CITGO COMPRESSORGARD[®] PAO



DESCRIPTION: CITGO CompressorGard PAO lubricants are formulated with high-quality polyalphaolefin (synthesized hydrocarbon) base fluids and incorporate technologically advanced additives to provide effective and efficient compressor performance. Available in ISO grades 32, 46, 68, 100 and 150.

BENEFITS: • Reduced danger of compressor fire and explosions resulting from deposit formation

- Outstanding oxidation and thermal stability
- · Exceptionally low pour point
- · Low varnish-forming tendencies
- Wide operating temperature range
- High viscosity index
- · Excellent antiwear properties
- · Extended service life
- Lower maintenance costs
- Excellent rust protection
- Fully compatible with elastomers, paints, seals and petroleum oil
- Low toxicity

Ρ

- Excellent demulsibility
- **APPLICATIONS:** CITGO CompressorGard PAO lubricants are designed for use with the following types of compressors: Rotary Vane, Rotary Screw and Centrifugal.

Rotary Compressors — Rotary vane and rotary screw compressors are lubricated by injecting the oil directly into the airstream where it is in intimate contact with high-temperature air. The excellent thermal and oxidation properties of CITGO CompressorGard PAO lubricants make them ideal to guard against sludge and varnish deposit formation and accumulation. They give outstanding performance in maintaining a cleaner compressor interior, which means reduced component wear and, thus, increased compressor efficiency and safety.

Centrifugal Compressors — Centrifugal (Dynamic) compressors are often mated with integral gear sets, requiring a lubricant with good load carrying ability and low foaming tendencies. These compressors are often remotely located. CITGO CompressorGard PAO lubricants contain a carefully selected and proven additive package and low vapor forming tendencies to assure that excellent performance can be achieved over an extended drain interval and extended compressor life when compared to petroleum oil.

(Continued)

CITGO Petroleum Corporation • 800/248-4684 • Houston, Texas • Manufactured in USA C10094

CITGO COMPRESSORGARD[®] PAO



TYPICAL PROPERTIES:

CITGO COMPRESSORGARD [®] PAO					
ISO Grade	32	46	68	100	150
Material Code	632531001	632532001	632533001	632534001	632535001
API Gravity Specific Gravity Density, Ib/gal, 60/60°F Viscosity, ASTM D445	36.6 0.842 7.01	35.8 0.847 7.04	36.4 0.843 7.02	35.8 0.847 7.04	34.8 0.851 7.09
cSt at 40°C cSt at 100°C	30.22 5.77	43.38 7.48	66.33 10.26	98.35 14.10	153.98 20.22
Viscosity Index, ASTM D2270 Flash Point, ASTM D92, °F (°C) Pour Point, ASTM D97, °F (°C)	136 522 (272) -87 (-66)	139 504 (262) -71 (-57)	141 543 (284) -65 (-54)	147 550 (288) -65 (-54)	152 550 (288) -54 (-48)
Color, ASTM D1500 Copper Corrosion, ASTM D130 Rust Protection, ASTM D665	L0.5 1A	L0.5 1A	L0.5 1A	L0.5 1A	L0.5 1A
DI Water Salt Water	Pass Pass	Pass Pass	Pass Pass	Pass Pass	Pass Pass
mm at 40 Kg Foam Resistance, ASTM D892	0.41	0.42	0.30	0.32	0.33
Sequence I, II, III Water Separation, ASTM D1401	Pass	Pass	Pass	Pass	Pass
at 130°F (54°C) at 180°F (82°C)	40/40/0 (5) -	40/40/0 (10) -	40/40/0 (10) -	- 40/40/0 (10)	- 40/40/0 (15)
Carbon Residue, mg	0.02	0.02	0.04	0.03	0.04

CompressorGard PAO lubricants are not compatible with silicone or polyalkylene glycol compressor lubricants. Consider CompressorGard PAG lubricants when compressing gases with condensed hydrocarbon liquids.

CITGO and CompressorGard are registered trademarks of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners.